

ADINGPOKS-N

Epoxy-based, solvent free adhesive for structural bonding between new and existing concrete. In compliance with: EN 1504-4/4.4

Field of Application:

Structural adhesive used for bonding fresh concrete or mortar and existing (hardened) concrete or other construction material. Adingpoks-N achieves adhesion higher than the tensile strength of the concrete.

Typically, it is used for preparation of construction joints (brakes between different phases of concreting), bonding new concrete screeds/plates on existing concrete substrate, or reparation, replacement or strengthening of damaged concrete or reinforced concrete sections - during reparations.

Adingpoks-N is also used for grouting of anchors.

Properties:

- Three component mixture;
- No shrinkage during material setting;
- Excellent adhesion to various substrates;
- High mechanical performances;
- High compression strength;
- High tensile and share strength;
- Applicable on moist and water-dumped substrate;
- Waterproofed;
- Ecological, solvent-free

Technical characteristics:

Appearance A com: Light brown viscous liquid

Appearance B com: Amber-coloured viscous liquid

Appearance C com: Quartz sand

Mixing ratio: A:B:C=3:1:2

Mixture specific weight: 1400-1500 kg/dm³

Application temperature: 5°C to 30 °C

Compression strength

According EN 12190: ≥30 Mpa

Adhesion strength ≥2 Mpa; Crash in

According EN 12636: concrete

Share strength

According EN 12615: \geq 6 Mpa Open workability time T=23°C 1-2 hours

METHOD STATEMENT:

Substrate preparation:

Proper substrate preparation is essential for establishing structural bond between layers that are bonded.

Concrete substrate, on which Adingpoks-N is applied need to have high mechanical properties, to be clean, all unstable sections need to be mechanically removed (using water or send blasting). Residues of grease, existing coatings ant other pollution need to be removed. During application of material, there must not be water dumped on the surface of the concrete.

Ambient and substrate temperature during application of material need to be between +10°C дo +30°C.

Application:

Material is prepared by mixing A and B component individually, than inter-mixed in clean and dry metal bucket. Two components are mixed in precise ratio, using slow electrical mixer (max 300-500 rotation/min). Powdery component - C is gradually added in the mix with constant mixing until complete homogenization. Application of material is conducted with metal trowel or hard brush in layers 1-2mm thick. Fresh concrete is applied until Adingpoks-N is still fresh and sticky when touched (30-60 after application depending on the temperature). In case if Adingpoks-N set before new cement/concrete mixture is applied, prior to concreting it is necessary to apply new layer of Adingpoks-N using the same procedure.

Consumption:

1

Material consumption depends of absorption and roughness (texture) of the substrate. Furthermore, consumption depends on the application temperature (at low temperatures, material thickness and consumption increases).

Consumption for layer 1,0mm thick: 1,4-1,5 kg/m²

ADINGPOKS-N 1/2



Anchor grouting:

In case Adingpoks-N is used for steel anchor grouting, anchor halls need to be minimum 5mm wider than the anchor, cleaned from dust with compressed air. Depending on the diameter and the position of the anchor hall, Adingpoks-N can be prepared using smaller quantity (or without) C-component (quartz sand), in order to achieve higher flow ability of material and easier filling of the space between steel anchor and the surrounding concrete. Prepared material Adingpoks-N is pored in the opening (filing approximately 1/2 of the depth) than anchor is forced in spilling excess material from the hall. Alternatively, when material can be applied by grouting-poring in the hall, in which case opening must be minimum 10mm wider than the anchor.

Cleaning:

Tools and equipment are cleaned with Solvent-P immediately after use.

Packing:

Set 6,6 kg Set 21 kg

A component: 3,3 kg
B component: 1,1 kg
C component: 2,2 kg

A component: 10,5 kg
B component: 3.5 kg
C component: 7 kg

Storage:

In original, closed packing, in dry chambers, at temperatures from +10 to +30 $^{\circ}\text{C}$. Shelf life 9 monts.

<u>Health hazard</u>: It is necessary to avoid contact of the product with skin or the eyes, as well as direct inhalation during mixing of components. In case of contact with skin material must be cleaned with dry towel or towel dip in Solvent-P, than skin must be cleaned with soap and water . If material get in contact with the eyes, it is necessary to clean with lot of water and to ask for medical assistance. Closed space or chambers in which material is prepared or applied, must be suppled with ventilation system.

Fire: Adingpoks-N and Sopvent-P containes flamable solvents. They must not be used near the open flames, or to smoke during preparationand application.

Cleaning and discarding: Loose residues of Adingpoks-N are cleaned with Solvent-P. Used package need to be disposed according to local regulations. It is recommended to ajust prepared quantities with conditions on the construction site, as well as to use appropriate protection equipment.

ADING



